

BE WRITE REPORT



NUSANTARA TECHNOLOGIES SDN. BHD. (187753-D)

No. 5, Jalan Anggerik Mokara 31/45, Seksyen 31, Kota Kemuning, 40460 Shah Alam, Selangor Darul Ehsan, Malaysia.

Tel: 03-5122 9766/7/8 Fax: 03-5122 8766/7 E-mail: info@nusatek.com

Our Ref.: NT/103542/18-02

Page No: 1 of 1

Report No: NDT/RT/180425-02/18

RADIOGRAPHIC EXAMINATION REPORT

Client and Testing Particulars

Client :	JP Consultancy & Engineering Sdn Bhd	Procedure No:	NT/G/RT/AWS Rev2.0
Project :	WPS / PC / SMAW / 001	IQI type :	ASTM 1B
Material:	S 355 JR	Film Manufacturer/Type :	FUJI 100(class II)
Welding Process :	SMAW	Density :	2.0 - 3.5
Examination Code :	AWS D1.1	Sensitivity:	0.33mm(5 wires visible)
Acceptance Code:	AWS D1.1	Source to Object Distance :	400mm
Examination Date:	19 April 2018	Source Side of Object to Film Distance:	(20+3)mm
		No of Radiograph(exposure) :	Single Exposure
		No. of Film Each Cassette :	1 Film
		Radiographic Technique :	DWSI
		Film Viewing Technique :	Single Wall Viewing
		Source Type/Size :	Iridium192 (3.2mm)
		Location Markers :	Film Side

Radiographic Examination Result

Weld Reference	WT	RT	Pipe Diameter	Material Thickness	Film Position	Film Interpretation	Result	Remarks
	(mm)	(mm)	(mm)	(mm)				
Saifullah Bin Saibi 881011-10-5055 4G	23	3	-	20	0 - 1	Por	Accept	

End of Report

Legend:

TI: Tungsten Inclusion	NRI: No Relevant Indication	Uc: Undercut	Por: Porosity	WT: Weld Thickness
SI: Slag Inclusion	LP: Lack of Penetration	Con: Concavity	BT: Burn Through	RT: Reinforcement Thickness
LF: Lack of Fusion	EP: Excess Penetration	AR: Artifact	Sur: Surface	

Personnel Particulars

Radiographer : Azizul - ASNT Lev. II

Interpreted & Evaluated By: Amat Hamidi - ASNT Lev.II

Date: 20 April 2018



Client Representative:

Name:

Date: